
| GUANGDONG BOSHUN BELTING CO.,LTD. | | | |
|-------------------------------------|---------------------------------------|--------------------------|-----------------|
| 博力顺 | Produ | uct Data | Sheet |
| BO LI SHUN | Type: P2-S20/31DA | | |
| | - | | |
| Main industry segments Treadmill | | | |
| Applications | | | Color code |
| Treadmill belt | | | RAL 9011 |
| Product structure | | | |
| Top cover | | | |
| -Thickness | 0.5 mm | | |
| -Material | Polyvinyl chloride (P | VC) | |
| -Features | Non adhesive surface, Medium friction | | |
| -Color | Black | 1 | |
| -Surface | Sandblast | | |
| -Hardness | 65° ShoreA | | |
| Bottom cover | | | |
| -Thickness | 0.5 mm | | |
| -Material | Polyester monofilam | ent | |
| -Features | | nt construction, Antista | atic, Low noise |
| -Color | - | | / |
| -Surface | Twill fabric | | |
| -Hardness | - | | |
| Technical data | | | |
| Total thickness | 2.0 mm | | |
| Number of plies | 2 | | - |
| Weight | 2.3 kg/m ² | | - |
| Maximum width | 2000 mm | | - |
| Effective pull at 1% elongation | 6 N/mm | | |
| Twisting force | 9.6 N/mm | | |
| Maximum admissible tension | 9 N/mm | | |
| Breaking strength | 80 N/mm | | |
| Temperature range | -15 °C ~ +80 °C | | |
| Minimum roll diameter | | | — |
| Normal flexion | 25 mm | | |
| Counter flexion | 35 mm | | |
| | 55 11111 | | |
| Characteristic | | | |
| Slide | Yes | Flame retardant | No |
| Roller | Yes | Cold resistant | No |
| Trough | No | Knife edges | No |
| Antistatic | No | Curves | No |
| Oil and fat resistant | No | Guides | No |
| FDA | No | Cleats | No |
| Low noise | Yes | Sidewalls | No |



Disclaimer

All data are approximate values and defined under the following standard climatic conditions. 23 °C, 50 % relative humidity (ISO 554).

All informations are recommendations and believed to be reliable, but no representations, guarantees, or warranties of any kind are made as to their accuracy or suitabbility for particular applications. Due to the fact that Boshun Belting has no control of use, we will not assume any liability concerning the suitability and process ability of the products mentioned herein. This also applies to defects, damages, consequential damages, and other consequences

Issued: 2019.04.29

Last update: 2019.05.16

www.boshunbelting.com

info@boshunbelting.com